

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Neopox[®] Primer WS

Two-component, solvent-free, epoxy primer for damp surfaces

Fields of application Floors (of factories, laboratories, warehouses, superstores, parking places, garages, slaughterhouses, larders, hospitals, schools, etc.), where the concrete is damp and water is gathered in the pores providing sufficient bonding to the surface. Also suitable for stabilization of old cement-based surfaces.

Properties

- Two-component, solvent-free epoxy primer with very strong adhesion on cement based substrates.
- It offers good resistance to alkalis.
- Suitable for interior use.
- May be applied to damp or moist porous surface.
- Can be used as a clear sealer.

Technical characteristics

Mixing ratio (weight proportion)	6.25A : 3.75B
Appearance	Gloss, clear, yellowish
Density (EN ISO 2811.01)	Component A: 1,14gr/cm ³ Component B: 1,01gr/cm ³
Consumption	200-300gr/m ² , for one coat (depending on substrate absorptivity)
Temperature of application	>+5°C
Relative humidity of application	≤99%
Drying time (25°C)	12 hours
Dry to recoat (25°C)	After 24 hours
Pot life (25°C)	20 minutes
Walkability (25°C)	24 hours
Total hardening	~7 days
Adhesion Strength (EN 13892-8)	≥3,0N/mm ²

Instruction for use *Surface preparation:* The surface should be also free from dust, dirt, greasy and oily substances. Therefore, it should be brushed, grinded or sandblasted and after that cleaned with vacuum cleaner. Moreover, imperfections of new surfaces should be smoothed with pulveriser for lower material consumption and



ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Neopox[®] Primer WS

achieving better adhesion properties.

Application: **Neopox[®] Primer WS** is applied in one layer with roller or brush. Before priming, the primer components A&B should be added and stirred thoroughly with low revolution mixer (2-3 minutes).

Special notes

- Low temperatures and high humidity during application prolong drying time, etc.
- Allow at least 4 weeks to pass between casting new concrete structures and painting them with the product

Cleaning of tools

Use solvent **Neotex[®] 1021** immediately after application.

Stain removal

Use solvent **Neotex[®] 1021** when the stain is still fresh and damp. In case of hardened stains, use mechanical means.

Packing

Sets of 10 kg in tin cans (components A&B have fixed weight proportion).

Storage stability

At least 3 years (+5°C to +45°C) in sealed tin cans .

